

STEP-BY-STEP

CONCRETE FLOOR

MICROCEMENT FOR FLOORS AND WALLS

LUXURY
CONCRETE

Non absorbent surfaces: CERAMIC TILES/TERRAZZO/MARBLE...

Absorbent surfaces: CEMENT/SELF LEVELING SCREED...

1

FILL THE JOINTS

Fill in the joints with Concrete Base
Drying Time: 24 hours
Sand: Grit 40

Primacrete ABS

1 layer as primer
Drying Time: 30 minutes

2

PRIMACRETE PLUS + MESH

1 layer as primer sticking the mesh
Drying Time: 30 minutes / max. 24 hours

CONCRETE BASE + MESH

1 layer without pigment sticking the mesh
Drying Time: 3 hours
Sand: Grit 40

3

CONCRETE BASE

1 layer without pigment
Drying Time: 12 hours
Sand: Grit 40

CONCRETE BASE

1 layer with pigment
Drying Time: 24 hours
Sand: Grit 40

4

PRIMACRETE PLUS (only ceramic tiles)

1 layer for equalising the absorption
Drying Time: 30 minutes/max. 24 hours

CONCRETE FLOOR

2 layers with pigment
Drying Time: 1st layer: 3h /6h - 2nd layer: 24h
Sand: Grit 80

5

CONCRETE BASE

1 layer with pigment
Drying Time: 24 hours
Sand: Grit 40

PRIMACRETE FINISH

2 layers
Drying Time: 4 hours between layers
Sand: Grit 400

6

CONCRETE FLOOR

2 layers with pigment
Drying Time: 1st layer: 3h /6h - 2nd layer: 24h
Sand: Grit 80

CONCRETE FINISH WT

2 layers
Drying Time: 24 hours between layers
Sand: Grit 400 (only 1st layer)

7

PRIMACRETE FINISH

2 layers
Drying Time: 4 hours between layers
Sand: Grit 400

8

CONCRETE FINISH WT

2 layers
Drying Time: 24 hours between layers
Sand: Grit 400 (only 1st layer)

Check the mix and consumption in the attached document.
24 hours = Next day

LUXURY
CONCRETE

Luxury Concrete SL / B98177538
C/ Lepanto 9, 3
46008 Valencia, España
+34 910 028 940
info@luxuryconcrete.eu
www.luxuryconcrete.eu

STEP-BY-STEP

CONCRETE FLOOR

MICROCEMENT FOR FLOORS AND WALLS

LUXURY
CONCRETE

MIX AND CONSUMPTION

Product	Mix	Consumption
Primacrete Plus		11 m ² / L
Primacrete ABS		10 m ² / L
Concrete Base	1 kg - 0,30 L resin	2 layers - 0,5 m ² /Kg
Concrete Floor	1 kg - 0,30/0,35 L resin	2 layers 1 m ² / kg
Primacrete Finish		2 layers 8,33 m ² / L
Concrete Finish WT	5 L(A) -1 L (B)	2 layers 6,67 m ² / L

Apply this product at ambient temperature between 10°C and 30°C.

LUXURY
CONCRETE

Luxury Concrete SL / B98177538
C/ Lepanto 9, 3
46008 Valencia, España
+34 910 028 940
info@luxuryconcrete.eu
www.luxuryconcrete.eu