

STEP-BY-STEP

CONCRETE POOL

MICROCEMENT FOR SWIMMING POOLS

LUXURY
CONCRETE

Surface: SHOTCRETE

1

Concrete Resin
Drying Time : 30 minutes

2

Concrete Pool Extra
1 layer without pigment
Drying Time: 4-8 hours
Sand: Grit 40

3

Concrete Pool Extra
1 layer with pigment
Drying Time: 4-8 hours
Sand: Grit 40

4

Concrete Pool Grand
2 layers with pigment
Drying Time: 24h each layer
Sand: Grit 80

5

Concrete Finish WT Pool
2 layers
Drying Time : 4-8 hours between layers
Applied with roller

Drying time before filling up the pool: 7 days.

Check the mix and consumption in the attached document.

24 hours = Next day.

LUXURY
CONCRETE

Luxury Concrete SL / B98177538
C/ Lepanto 9, 3
46008 Valencia, España
+34 910 028 940
info@luxuryconcrete.eu
www.luxuryconcrete.eu

STEP-BY-STEP

CONCRETE POOL

MICROCEMENT FOR SWIMMING POOLS

LUXURY
CONCRETE

MIX AND CONSUMPTION

Product	Mix	Consumption
Concrete Resin Pool		1 layers 0,10 L/m ²
Concrete Pool Grand	1 kg - 0,25 L resin	2 layers 3,0 Kg/m ²
Concrete Pool Extra	1 kg - 0,30 L resin	2 layers 5,2 Kg/m ²
Concrete Finish WT Pool		2 layers 0,12 L/m ²

Apply this product at ambient temperature between 10°C and 30°C.

LUXURY
CONCRETE

Luxury Concrete SL / B98177538
C/ Lepanto 9, 3
46008 Valencia, España
+34 910 028 940
info@luxuryconcrete.eu
www.luxuryconcrete.eu