

# STEP-BY-STEP

## CONCRETE WALL

MICROCEMENT FOR WALLS

LUXURY  
CONCRETE

	NON ABSORBENT SURFACES: CERAMIC TILES	ABSORBENT SURFACES: PLASTERBOARD	ABSORBENT SURFACES: CEMENT
<b>1</b>	<b>FILL THE JOINTS</b> Fill in the joints with Concrete Base <b>Drying Time:</b> 24 hours <b>Sand:</b> Grit 40	<b>Primacrete ABS</b> <b>Drying Time:</b> 30 minutes	<b>Concrete Resin</b> <b>Drying Time:</b> 30 minutes
<b>2</b>	<b>PRIMACRETE PLUS + MESH</b> 1 layer as primer sticking the mesh <b>Drying Time:</b> 30 minutes / max. 24 hours	<b>CONCRETE BASE + MESH</b> 1 layer without pigment sticking the mesh <b>Drying Time:</b> 3 hours <b>Sand:</b> Grit 40	<b>CONCRETE BASE + MESH</b> 1 layer without pigment sticking the mesh <b>Drying Time:</b> 3 hours <b>Sand:</b> Grit 40
<b>3</b>	<b>CONCRETE BASE</b> 1 layer without pigment <b>Drying Time:</b> 12 hours <b>Sand:</b> Grit 40	<b>CONCRETE BASE</b> 1 layer with pigment <b>Drying Time:</b> 24 hours <b>Sand:</b> Grit 40	<b>CONCRETE BASE</b> 1 layer with pigment <b>Drying Time:</b> 24 hours <b>Sand:</b> Grit 40
<b>4</b>	<b>PRIMACRETE PLUS (only ceramic tiles)</b> 1 layer for equalising the absorption <b>Drying Time:</b> 30 minutes/max. 24 hours	<b>CONCRETE WALL</b> 2 layers with pigment <b>Drying Time:</b> 3 h (1 <sup>st</sup> layer) - 24h (2 <sup>nd</sup> layer) <b>Sand:</b> Grit 120 (sanding machine) / 220 (by hand)	<b>CONCRETE WALL</b> 2 layers with pigment <b>Drying Time:</b> 3 h (1 <sup>st</sup> layer) - 24h (2 <sup>nd</sup> layer) <b>Sand:</b> Grit 120 (sanding machine) / 220 (by hand)
<b>5</b>	<b>CONCRETE BASE</b> 1 layer with pigment <b>Drying Time:</b> 24 hours <b>Sand:</b> Grit 40	<b>PRIMACRETE FINISH</b> 2 layers <b>Drying Time:</b> 4 hours between layers <b>Sand:</b> Grit 400	<b>PRIMACRETE FINISH</b> 2 layers <b>Drying Time:</b> 4 hours between layers <b>Sand:</b> Grit 400
<b>6</b>	<b>CONCRETE WALL</b> 2 layers with pigment <b>Drying Time:</b> 3 h (1 <sup>st</sup> layer) - 24h (2 <sup>nd</sup> layer) <b>Sand:</b> Grit 120 (sanding machine) / 220 (by hand)	<b>CONCRETE FINISH WT</b> 2 layers <b>Drying Time:</b> 24 hours between layers <b>Sand:</b> Grit 400 (only 1st layer)	<b>CONCRETE FINISH WT</b> 2 layers <b>Drying Time:</b> 24 hours between layers <b>Sand:</b> Grit 400 (only 1st layer)
<b>7</b>	<b>PRIMACRETE FINISH</b> 2 layers <b>Drying Time:</b> 4 hours between layers <b>Sand:</b> Grit 400		
<b>8</b>	<b>CONCRETE FINISH WT</b> 2 layers <b>Drying Time:</b> 24 hours between layers <b>Sand:</b> Grit 400 (only 1st layer)		

Check the mix and consumption in the attached document.  
24 hours = Next day

# STEP-BY-STEP

## CONCRETE WALL

MICROCEMENT FOR WALLS

LUXURY  
CONCRETE

### MIX AND CONSUMPTION

Product	Mix	Consumption
Primacrete Plus		11 m <sup>2</sup> / L
Primacrete ABS		10 m <sup>2</sup> / L
Concrete Base	1 kg - 0,30 L resin	2 layers - 0,5 m <sup>2</sup> /Kg
Concrete Wall	1 kg - 0,45 L resin	2 layers - 2 m <sup>2</sup> / kg
Primacrete Finish		2 layers - 8,33 m <sup>2</sup> / L
Concrete Finish WT	5 L(A) -1 L (B)	2 layers - 6,67 m <sup>2</sup> / L

Apply this product at ambient temperature between 10°C and 30°C.